



*We help you
invent the future.™*

dowcorning.com

Silicones Simplified

www.xiameter.com



Fluid Resistance Guide

Performance Profiles for XIAMETER® brand Silicone Rubber

Contents	Page
Introduction	2
Fluids Index	4
ASTM and IRM Oils, Fuels, and Fluids	6
MIL Specification Oils, Fuels, and Fluids	8
Automotive Oils and Fluids	11
Fuels	14
Hydraulic Fluids	15
Transformer and Instrument Oils	17
Specialty Oils, Greases, and Fluids	18
Solvents	21
Silicone Fluids	23
Silicone Compounds and Greases	25
Food Products	26
Water and Steam	28
Acids	29
Bases	30
Salts	31
Other Chemicals	31

Introduction

This guide is intended to give you an idea of the performance profile of various classes of silicone rubbers when immersed in different fluids. It's our hope that the information will save you the time and cost of preliminary screening and feasibility tests. We recommend that you test specific materials prior to use. Keep in mind that service conditions are usually less severe than immersion tests. For instance, in actual service the rubber is often only partly exposed or is subjected only to spills or splashing. This means that a rubber that shows only fair results in a prolonged total immersion test will often perform quite adequately under actual conditions.

Types of XIAMETER® brand Silicone Rubbers

Immersion test results refer to types of silicone rubber by their ASTM designation. The polymer classification described in ASTM D 1418 is based on the organic group side chains attached to the silicon-oxygen chain. If other groups are present, their initials are listed prior to the MQ designation: MQ indicates methyl groups, V indicates phenyl groups. Where several types of rubber have been tested for resistance to one fluid, they are listed in this order in the tables:

XIAMETER brand Silicone Rubbers

MQ } General purpose stocks
VMQ }

PMQ } Extremely low-temperature stocks
PVMQ }

XIAMETER® brand Fluorosilicone Rubbers

FVMQ Fuel-, oil-and solvent-resistant stocks

Effects of Immersion

If a fluid affects a silicone rubber at all, after prolonged immersion and usually at elevated temperatures, the changes are evidenced as increases or decreases of several physical properties: hardness, tensile strength, elongation, and volume. The values that appear in the tables have been calculated as prescribed in ASTM D 471. The figures have been rounded and represent typical values. The effects that have been tabulated often go hand in hand, but there is no quantitative correlation. For example, a silicone rubber in one fluid may swell 10 percent and lose 15 percent in tensile strength, whereas in another fluid the same rubber may also swell 10 percent but lose 30 percent in tensile strength.

The effects of solvent or fuel immersion often proceed until they reach a limit and then increase no more. This limit corresponds to the maximum amount of solvent or fuel that the rubber structure can absorb at the test temperature. While a fluid may produce little effect at room temperature, it may cause a noticeable change at 204°C (400°F).

Swelling caused by fluid penetration of rubber is usually the most obvious effect. However, this swelling does not necessarily indicate permanent deterioration. The rubber often regains most of its original properties after the fluid has evaporated.

Hardness changes are tabulated in durometer points on the Shore A-2 scale. Changes in tensile strength and elongation are expressed as percentages of the original values. These changes are usually losses that appear as negative values. Volume changes due to penetration of fluids between silicone polymer chains appear as positive values, that is, swelling. Negative volume changes indicate chemical degradation, such as the tables show for 20 percent sulfuric acid at 83°C (180°F) for seven days.

Service Considerations

Duration of exposure may be very important in some applications. In the case of silicone rubber used as electrical insulation, this may mean that no permanent harm will result from short exposures to washing or rinsing, even with powerful solvents. After prolonged periods at high temperatures, hydrocarbon oils may slowly decompose. The breakdown products may have an entirely different solvent effect than that of the original oil. On the other hand, heating may sometimes have the favorable result of driving off volatile components of oils. Contamination in service may also produce changes in lubricating oils and their effect as immersion media. Swelling may be a limiting factor in service, even though a small amount may be desirable for certain applications. For example, o-rings often work better if they swell slightly in the fluid they seal; but if they swell too much, they may push themselves out of position and lose effectiveness. Also, swelling may produce tears in tightly restricted parts.

Selection Recommendations

1. XIAMETER brand fluorosilicone rubber shows superior resistance to many fluids; however, other types of rubber offer better resistance to acetone, certain other ketones, and some esters. The fluorosilicone polymer can be blended with other silicone polymers to obtain resistance intermediate between the two types.

2. The higher the aromatic or phenyl content of oils and fuels, the greater is their effect on most types of silicone rubber except fluorosilicone rubber. The stocks most affected are usually the types with ASTM designations including P (phenyl groups). This follows the common principle of organic to solvents that "like dissolves like."

3. For high-temperature applications, parts should generally be cured at temperatures higher than anticipated service temperatures, no matter whether the parts will contact liquid or air. Property changes are usually less for fully cured parts than for as-vulcanized or partially cured parts.

Test Conditions

The immersion tests tabulated were conducted according to ASTM D 471. Specimens were cut from slabs that were molded and oven-cured in accordance with recommended procedures for the individual stocks.

Many fluids were tested only for their effects on volume and hardness because these values are usually the most critical.

In regard to the limited correlation between test conditions and service conditions, the most widely used test, ASTM D 471, states:

"Owing to the wide variations often present in service conditions, no direct correlation between this accelerated test and service performance may be given or implied. However, the method yields comparative data on which to base judgment (as to service quality and is especially useful in research and development work)."

Test results refer to types of silicone rubber products by ASTM designation. Because tests were conducted over a period of several years, the specific products used may no longer be available. Test results, therefore, can be used to project general performance only. If more specific information is required, refer to individual data sheets or conduct new tests.

Fluids Index

Classification of Immersion Media

Fluids for testing have often been submitted with only a trade name for identification. It has been difficult to classify some of these fluids for the tabular sections of this guide. The overall classification has been designed for easy reference by users in different industries.

A		Coca-Cola Syrup	26	G	
Acetic Acid	29	Coffee	26	Gas Drip Oil	19
Acetone	21	Coolanol 35	18	Gasohol	15
Acctonitrile	31	Coolanol 45	18	Gasoline	14
Aroclor 1254	19	Copper Sulfate	31	GE Transil Oil	19
Aerosafe 2300	15	Cosmoline 2046	19	GM Hydraniatic Fluid (Type A)	12
Ammonia	31	Crude Oil 7 API	19	GM 14X Heavy Duty Oil	19
Ammonium Hydroxide	30	Crude Oil 315 API	19	Gulf Synthetic Lube No. 2 Oil	10
AMOCO Super Permuable 10W-30	11	Cyclohexane	22	H	
ANG 15 Industrial Grease	18	D		Heptane	22
ANG 25 Diester Base	18	Delco No. 9	19	HMS 20-1083	33
ANG 25 Glycerol Ester	18	Delco No. 11	19	Hydrazine	33
Aniline	31	Delco Shock Absorber Fluid	13	Hydrochloric Acid	29
ANO No. 3 Grade M; Extreme Pressure	18	Delco Supreme 550 Heavy-Duty Brake Fluid	13	Hydrofluoric Acid	29
ANO No. 6 Oil	18	Diacetone Alcohol	22	Hydrogen Peroxide	33
ANO No. 9 Oil	18	Dichloroisopropyl Ether	22	Hydrolube H-2 Fluid	15
ANO No. 11 Oil	18	Diesel Fuel	14	Hypoid EP Lubricant	13
ANO No. 366 Oil	18	Diethyl Ether	22	I	
Aroclor 1254	19	Di (2-Ethylhexyl) Sebacate	7	Inerteen Transformer Oil	17
Askerol Transformer Oil	17	Dimethyl Formamide	32	IRM 902 Oil	7
ASTM No. 1 Oil	6	Diocetyl Phthalate	32	IRM 903 Oil	7
ASTM No. 2 Oil	6	Dowtherm A Heat Transfer Oil	19	Isooctane	7
ASTM No. 3 Oil	6	Dowtherm 209	32	Isopropyl Alcohol	22
ASTM reference fuel A Isoctane	7	<i>Dow Corning</i> [®] brand Compounds	25, 26	Isopropyl Nitrate	33
ASTM Reference Fuel B	8	<i>Dow Corning</i> [®] brand Fluids	24, 25	J	
ASTM Reference Fuel C	8	<i>Dow Corning</i> [®] brand Greases	25, 26	JP-4 Fuel	14
ASTM Test Fluid 101	7	Dynaflow Automatic Transmission Fluid	12	JP-5 Fuel	14
B		E		JP-8 Fuel	14
Beer	26	Ethanol	15	L	
Benzene	21	Ethyl Alcohol	22	Lard	26
Brayco 880D Oil	10	Ethylenedichloride	22	Lithium Hydroxide	30
Bromine (liquid)	31	Ethylene Glycol	32	M	
Butter (liquid)	26	Ethylene Oxide	32	Manufactured Gas	14
Butyl Acetate	22	Exxon Turbo Oil No. 15	9	Mazola Oil	26
Butyl Alcohol	22	Exxon Univis J-43 Oil	9	Methanol	8, 15
Butylene Oxide	31	Exxon WS2406 Fluid	15	Methyl Alcohol	22
C		F		Methyl Chloride	22
Calcium Oxide	30	FC-75 Fluorochemical Fluid	19	Methylene Chloride	22
Calcium Silicate	31	Ferric Chloride	31	Methyl Methacrylate	33
Caprolactam Monomer	31	Freon	32, 33	MIL-A-8243 Deicer Fluid	10
Carbon Tetrachloride	22			MIL-H-5606	9
Chlorobromomethane	22			MIL-H-5606 Oil	9
1-Chlorodecane	32			MIL-J-5624F-14	14
Chloroform	22				
Chlorothene Solvent	22				

MIL-L4600 Oil Bis	11	PQ 4226	9	Tetrahydrofuran	34
MIL-L-7808D Oil	9	PQ 8365	10	Texaco 10W 30 Motor Oil	11
MIL-L-7808E Oil	10	PRL 3313	20	Texaco Regal Starfak	
MIL-L-7808E, F, and G Oil	10	Propylenedichloride	23	Special Grease	18
MIL-L-7808F Oil	10	Propylene Oxide	34	Texaco TG-749	18
MIL-L-7808G Oil	10	Pydraul Fluids	16	Texamatic A Transmission Fluid	12
MIL-7808J Jet Engine Oil	11	Pyranol Transformer Oil	17	Texamatic C Transmission Fluid	12
MIL-L-23699 Oil	10	R		Texamatic TL 3528	
MIL-O-6085 Oil	9	RCA-Gulf Instrument Oil A	17	Transmission Fluid	12
Mineral Oil	19	Royco 808GF Oil	10	Texas 1500 Oil (HD Concentrate)	20
Mineral Oil (Shell No. 5)	19	RX-1099 (Vinyl Plastisol)	34	Tia Maria Liquor	27
Mineral Spirits	22	S		TL 3450 Lubricant	13
Mobil 5W-30HP Engine oil	11	SAE No. 10 Oil	11	Toluene	23
Mobil Jet II Oil	11	SAE No. 20 Oil	11	Toluene Vapor	23
Mobil Oil No. 20 Oil	11	Salicylanilide	34	TTS-735 Type VII	9
Mobilube GX-90 General Lubricant	13	Santicizer 141	34	Trichloroethylene	34
Mobil XRM-139A Oil	10	Scotch Whisky	27	Tricresyl Phosphate	21
Molybdenum Disulfide	33	SG 4766 Glycol Ester Base Grease	20	Trifluorochloroethylene	34
Monochlorobenzene	22	Shell Aircraft Turbine Lubricants	20	Turbo Oil No. 35	21
Monoethanolamine	33	Shell B & B Grease	20	Turpentine	23
Motor Oil - 10W-30	11	Skydrol Fluids	16, 17	XIAMETER® PMX-200	
N		Socony Mobil RL 147-A No. 7	20	Silicone Fluid	23, 24
Naphtha	23	Socony Mobil Transmission Fluid		U	
Navy Crankcase Oil No. 2135	20	(Type A)	12	Ucon Lubricants	21
Navy Crankcase Oil No. 9250	20	Sodium Carbonate	31	Univolt 35 Transformer Oil	17
N-43 Fluorocarbon Capacitor Fluid	17	Sodium Chloride	31	Unsymmetrical Dimethyl	
Nitric Acid 29,	30	Sodium Hydroxide	31	Hydrazine	15
Nitrocellulose Solvent	23	Solvatone Solvent	23	V	
No Lead Gasolines	15	Spry Shortening	27	Vegetable Oil	27
O		Standard Oil Shock		Vinegar	27
1-Chlorodecane	32	Absorber Fluid	13	W	
Oil	26, 27	Staufferjet II Oil	10	Wagner 21B Brake Fluid	13
Orange Peel Oil	26	Steam	28, 29	Water	28
Orange Syrup	27	Stoddard Solvent	23	Wemco C Transformer Oil	18
Oronite Fluids	15, 16	Styrene Monomer	34	White Gasoline Vapors	14
Ortho-Chloroethylbenzene	23	Sulfur	34	X	
Ortho-Chlorotoluene	23	Sulfur Dioxide	34	Xylene	23
Oxylene Solvent	23	Sullur Hexafluoride	34		
P		Sulfuric Acid	30		
Pacemaker Fluid 100T	20	Sun Oil No. 8 X2513-I L	20		
Pentachlorophenol	33	Sun 5W-3 Auto Engine Oil	11		
Perchloroethylene	23	Sun 109 Transmission Fluid	12		
Phenol	33	SUNOCO HD	11		
Phosphoric Acid	30	Swan Finch EP90 Lubricant	13		
Phthalic Acid Anhydride	33	T			
Phthalic Anhydride	33	Tab Concentrate	27		
Polyglycol	34	Tar	34		
Polystyrene	34	Tectyl 502C Rust Inhibitor	20		
Potassium Hydroxide	30	Tectyl 511-M Rust Inhibitor	20		

ASTM and IRM Oils, Fuels and Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
ASTM No. 1 Oil	VMQ	3 days/25°C (77°F)	nil	-	-	nil
	PVMQ		-5	-	-	5
	MQ	3 days/100°C (212°F)	-5	-5	-5	5
	VMQ		-5	-10	-5	5
	PVMQ		-10	-10	-10	10
	MQ	1 day/150°C (302°F)	-10	-10	5	5
	VMQ		-5	-10	-10	10
	PVMQ		-10	-15	-10	10
	MQ	3 days/150°C (302°F)	-10	-10	nil	5
	VMQ		-10	-5	-5	10
	PVMQ		-10	-20	-15	10
	FVMQ		-5	nil	-5	nil
	MQ	7 days/150°C (302°F)	-10	-10	-10	10
	VMQ		-10	-10	-10	10
	PVMQ		-10	-20	-10	10
	VMQ	30 days/150°C (302°F)	-10	-35	-25	10
	MQ	3 days/177°C (350°F)	-10	-10	-10	5
	VMQ		-5	-10	-10	10
PVMQ	-15		-20	-10	10	
VMQ	7 days/177°C (350°F) 14 days/177°C (350°F)	-20	-50	-30	10	
		-20	-50	-30	10	
ASTM No. 2 Oil	VMQ	70 hr/150°C(302°F)	-6	4	-2	1
	FVMQ		nil	nil	-14	1
	VMQ	7 days/150°C (302°F)	-6	8	nil	8
	FVMQ		-2	1	-13	1
ASTM No. 3 Oil	MQ	3 days/24°C (75°F)	-5	-	-	15
	PVMQ		-10	-	-	25
	MQ	3 days/100°C (212°F)	-10	-	-	20
	PVMQ		-15	-	-	35
	PVMQ	7 days/110°C(230°F)	-30	-75	-60	60
	FVMQ		-5	-5	-5	5
	MQ	1 day/150°C (302°F)	-20	-50	-20	50
	VMQ		-15	-35	-20	45
	PVMQ		-25	-40	-20	50
	FVMQ		-5	-10	10	5
	MQ	3 days/150°C (302°F)	-25	-50	-25	35
	VMQ		-20	-45	-25	35
	PVMQ		-35	-50	-30	55
	PVMQ		-25	-	-	85
	FVMQ		-5	-25	-10	5
	VMQ	7 days/150°C (302°F)	-25	-45	nil	40
	FVMQ		-5	-17	-15	5
	FVMQ	14 days/150°C (302°F) 21 days/150°C (302°F) 28 days/150°C (302°F)	-5	-25	5	5
	-10		-60	5	5	
	-10		-85	-20	5	

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

ASTM and IRM Oils, Fuels and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
ASTM No. 3 Oil (cont.)	VMQ	4 hr/177°C (350°F)	-25	-35	-25	45
	MQ	3 days/177°C (350°F)	-35	-85	-25	55
	VMQ		-40	-60	-15	60
	PVMQ		-40	-65	5	70
	FVMQ		-10	-25	5	5
	VMQ	7 days/177°C (350°F)	-50	-80	-30	70
	FVMQ		-10	-40	5	5
	VMQ	3 days/200°C (392°F)	-15	-45	nil	5
FVMQ	14 days/200°C (392°F)	-25	-40	-10	nil	
IRM-902 Oil	VMQ	3 days/23°C (73°F)	-5	-12	-14	5
	PVMQ		-8	-12	-12	7
	FVMQ		-6	-7	-1	1
	VMQ	3 days at 150°C (302°F)	-6	-7	-17	10
	PVMQ		-16	-7	-21	19
	FVMQ		0	-7	-8	1
IRM-903 Oil	VMQ	3 days/23°C (73°F)	-12	-7	-11	18
	PVMQ		-21	-31	-23	33
	FVMQ		-4	-7	-3	1
	VMQ	3 days/150°C (302°F)	-26	-23	-28	40
	PVMQ		-33	-68	-62	84
	FVMQ		-2	-11	-15	2
	FVMQ (70 Durometer)	70 hours/150°C (302°F)	-4	-8	4	2
		7 days/150°C (302°F)	-3	-9	6	2
ASTM Test Fluid 101 Di (2-Ethylhexyl) Sebacate +0.5% Phenothiozine Di (2-Ethylhexyl) Sebacate (Plexol-201)	FVMQ	7 days/135°C (275°F)	-4	-7	-11	5
		48 hr/150°C (302°F)	-10	-25	-25	10
	MQ	7 days/100°C (212°F)	-15	-	-	20
	VMQ		-10	-	-	20
	FVMQ	4 days/232°C (450°F)	DT	DT	DT	DT
ASTM Reference Fuel A - Isooctane (also TTS-735 Type I)	VMQ	5 min/-54°C (-65°F)	-	-	-	10
	PMQ		-	-	-	10
	PVMQ		-	-	-	10
	VMQ	10 min/-54°C (-65°F)	-	-	-	20
	PMQ		-	-	-	20
	PVMQ		-	-	-	15
	VMQ	30 min/-54°C (-65°F)	-	-	-	30
	PMQ		-	-	-	35
	PVMQ		-	-	-	30
	VMQ	5 min/24°C (75°F)	-	-	-	25
	PMQ		-	-	-	30
	PVMQ		-	-	-	25
	VMQ	10 min/24°C (75°F)	-	-	-	35
	PMQ		-	-	-	50
	PVMQ		-	-	-	40
	VMQ	30 min/24°C (75°F)	-	-	-	90
	PMQ		-	-	-	85
	PVMQ		-	-	-	75
	FVMQ	7 days/24°C (75°F)	-5	-40	-30	15
		3 days/150°C (302°F)	-20	-60	-30	25

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

ASTM and IRM Oils, Fuels and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
ASTM Reference Fuel B (70% Isooctane, 30% Toluene by Volume) (also TTS-735 Type III)	FVMQ	1 day/-54°C (-65°F)	-5	-20	-20	10
		3 days/24°C (75°F)	-5	-55	-35	20
		7 days/24°C (75°F)	-5	-40	-30	20
		14 days/24°C (75°F)	-10	nil	-30	15
	VMQ FVMQ	3 days/65°C (150°F)	-5	-50	-40	215 15
FVMQ	3 days/150°C (302°F) 3 days/232°C (450°F)	-20 DT	-60 DT	-35 DT	30 DT	

MIL Specification Oils, Fuels and Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
ASTM Reference Fuel C (M0)	FVMQ (60 Durometer)	1 day/23°C (73°F)	-15	-25	-23	18
		1 week/23°C (73°F)	-14	-20	-19	19
		3 months/23°C (73°F)	-14	-23	-20	19
		1 year/23°C (73°F)	-13	-22	-18	19
		1 day/60°C (140°F)	-14	-30	-15	21
		1 week/60°C (140°F)	-14	-36	-32	21
		3 months/60°C (140 F)	-17	-37	-28	22
		6 months/60°C (140°F)	-14	-33	-35	21
85% ASTM Reference Fuel C 15% Methanol (M15)	FVMQ (60 Durometer)	1 day/23°C (73°F)	-24	-52	-29	26
		1 week/23°C (73°F)	-18	-56	-42	24
		3 months/23°C (73°F)	-18	-50	-38	25
		1 year/23°C (73°F)	-14	-53	-38	24
		1 day/60°C (140°F)	-21	-57	-41	29
		1 week/60°C (140°F)	-21	-64	-48	31
3 months/60°C (140°F)	-24	-64	-45	31		
75% ASTM Reference Fuel C 25% Methanol (M25)	FVMQ (60 Durometer)	1 day/23°C (73°F)	-19	-53	-43	26
		1 week/23°C (73°F)	-19	-54	-40	25
		3 months/23°C (73°F)	-18	-50	-39	25
		1 year/23°C (73°F)	-13	-51	-36	24
		1 day/60°C (140°F)	-20	-63	-51	32
		1 week/60°C (140°F)	-23	-62	-48	33
		3 months/60°C (140°F)	-26	-68	-48	33
6 months/60°C (140°F)	-27	-64	-45	28		
50% ASTM Reference Fuel C 50% Methanol (M50)	FVMQ (60 Durometer)	1 day/23°C (73°F)	-18	-52	-41	25
		1 week/23°C (73°F)	-18	-48	-37	24
		3 months/23°C (73°F)	-19	-49	-39	23
		1 year/23°C (73°F)	-17	-50	-33	22
		1 day/60°C (140°F)	-21	-60	-47	29
		1 week/60°C (140°F)	-22	-59	-46	30
3 months/60°C (140°F)	-24	-64	-43	28		
15% ASTM Reference Fuel C 85% Methanol (M85)	FVMQ (60 Durometer)	1 day/23°C (73°F)	-15	-36	-27	14
		1 week 23°C (73°F)	-14	-37	-19	13
		3 months/23°C (73°F)	-11	-32	-21	11
		1 year/23°C (73°F)	-11	-38	-20	11
		1 day/60°C (140°F)	-17	-38	-24	15
		1 week/60°C (140°F)	-18	-42	-20	14
		3 months/60°C (140°F)	-17	-49	-25	12
6 months/60° C (140°F)	-15	-50	-31	8		
60% ASTM Reference Fuel C 40% Methanol by Volume (M40)	FVMQ (75 Durometer)	24 hours/110°C (230°F)	-30	-66	-50	46

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

MIL Specification Oils, Fuels and Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
TTS-735 Type VII (30% Toluene, 10% Isooctane, 59% Cyclohexane, 1.0% n-Butyl Disulfide)	FVMQ	3 days/24°C (75°F)	-10	-40	-25	20
		3 days/100°C (212°F)	-10	-40	-35	20
MIL-H-5606 Oil (Exxon Univis J-43)	VMQ	14 days/24°C (75°F)	-	-	-	65
	PVMQ		-	-	-	95
	MQ	1 day/71°C (160°F)	-20	-75	-60	160
	PMQ		-30	-65	-55	120
	FVMQ		-5	-30	-10	5
	FVMQ	3 days/71°C (160°F)	-10	-30	-15	5
	VMQ	14 days/71°C (160°F)	-	-	-	80
	PVMQ		-	-	-	110
	FVMQ	19 days/121°C (250°F)	-10	-10	-15	5
		3 days/150°C (302°F)	-10	-35	-10	10
		3 days/177°C (350°F)	-20	-50	-10	10
		7 days/177°C (350°F)	-20	-55	5	10
	3 days/200°C (392°F)	-35	-85	15	15	
MIL-H-5606 (American Oil PQ 4226)	FVMQ	70 hr/150°C (302°F)	-6	-8	-16	6
MIL-O-6085 Oil	FVMQ	14 days/177°C (350°F)	-20	-70	-15	10
MIL-L-7808D Oil (Exxon Turbo Oil No. 15)	FVMQ	1 day/-54°C (-65°F)	-5	-15	nil	nil
	MQ	3 days/24°C (75°F)	-5	-10	nil	10
	VMQ		-10	-10	-5	10
	PMQ		-10	-25	-15	20
	PVMQ	3 days/24°C (75°F)	-15	-10	-5	20
		7 days/24°C (75°F)	-25	-55	-40	30
	VMQ	3 days/71°C (160°F)	-15	-10	-10	15
	PMQ		-15	-45	-40	30
	MQ	7 days/71°C (160°F)	-10	-	-	15
	VMQ		-10	-	-	15
	PMQ		-20	-	-	30
	PVMQ		-25	-65	-50	35
	MQ	1 day/121°C (250°F)	-10	-	-	20
VMQ		-10	-	-	20	
PMQ		-10	-	-	40	
VMQ	3 days/121°C (250°F)	-10	-25	-20	20	
FVMQ		-5	nil	nil	5	

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

MIL Specification Oils, Fuels and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
MIL-L-7808D Oil (Exxon Turbo Oil No. 15)	MQ	1 day/150°C (302°F)	-10	-	-	15
	VMQ		-5	-	-	10
	PMQ		-10	-	-	20
	VMQ	3 days/150°C(302°F)	-15	-40	-10	25
	PVMQ		-25	-45	5	40
	FVMQ		-5	-15	nil	10
	MQ	1 hr/177°C (350°F)	-10	-	-	10
	FVMQ	1 day/177°C (350°F)	-10	-35	-10	10
	MQ	3 days/177°C (350°F)	-30	-65	-5	35
	VMQ		-35	-	-	30
	PMQ		-25	-50	-15	45
	PVMQ		-35	-55	-15	50
	FVMQ		-15	-40	-10	5
	FVMQ	7 days/177°C (350°F) 14 days/177°C (350°F) 1 day/200°C (392°F)	-20 DT -30	-60 DT -70	nil DT -15	10 DT 15
VMQ	3 days/200°C (392°F)	-35	-	-	30	
FVMQ		-45	-95	-45	15	
MIL-L-7808E Oil (Brayco 880D)	VMQ	70 hr/150°C (302°F)	-20	-35	-10	25
	FVMQ		-5	-80	-60	5
	VMQ	70 hr/177°C (350°F)	-35	-75	-30	25
	FVMQ		-5	-95	-90	-5
MIL-L-7808E, F, and G Oil (StaufferJet I)	VMQ	70 hr/150°C (302°F)	-20	-25	-10	25
	FVMQ		-10	-25	-25	10
	VMQ	70 hr/177°C (350°F)	-35	-65	-10	35
	FVMQ		-15	-60	-35	10
MIL-L-7808F Oil (Gulf Synthetic Lube No. 2)	FVMQ	70 hr/150°C (302°F)	-10	-30	-15	15
MIL-L-7808F Oil (Royco 808GF)	FVMQ	70 hr/150°C (302°F)	-10	-45	-15	10
	FVMQ	70 hr/177°C (350°F)	-20	-60	-20	15
MIL-L-7808F Oil (Brayco 880G)	FVMQ	70 hr/150°C (302°F)	-15	-30	-20	10
MIL-L-7808G (Amendment 2) PQ8365	VMQ	70 hr/150°C (302°F)	-14	-21	-19	25
	FVMQ		-8	-9	-24	8
MIL-A-8243 Deicer Fluid	PVMQ	70 hr/71°C (160°F)	-5	-15	-10	nil
MIL-L-23699 Oil (Mobil XRM-139A)	FVMQ	96 hr/177°C (350°F)	-15	-	-	10
StaufferJet II Oil	FVMQ	70 hr/177°C (350°F)	-8	-25	-21	12
	VMQ	100 hr/177°C (350°F)	-9	2	42	11
	FVMQ		-9	-19	-36	12
	VMQ	300 hr/177°C (350°F)	-8	-3	50	7
	FVMQ		-15	-73	-33	9

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

ASTM and MIL Specification Oils, Fuels and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Mobil Jet II Oil	VMQ	22 hr/25°C (77°F)	-	-	-	4
	FVMQ		-	-	-	3
	VMQ	70 hr/150°C (302°F)	-10	10	15	10
	FVMQ		nil	20	-35	10
	VMQ	7 days/1500C(302°F)	-10	10	25	10
	FVMQ		nil	5	-35	10
MIL-L-4600 Oil Bis (2-Ethylhexyl) Sebacate	PVMQ	3 days/25°C (77°F)	-14	-	-	28
		7 days/25°C (77°F)	-14	-	-	30
MIL-L-7808JJet Engine Oil	75% FVMQ 25% VMQ Blend.	22 hours/24°C (75°F)	-6	-28	-22	4

Automotive Oils and Fluids

Motor Oils

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
SAE No. 10 Oil (Sunoco HD)	FVMQ	3 days/150°C (302°F)	-5	-5	nil	nil
	MQ	1 day/100°C (212°F)	-	-	-	10
	PMQ		-	-	-	20
SAE No. 20 Oil (Mobil Oil)	MQ	1 day/121°C (250°F)	-	-	-	15
	PMQ		-	-	-	25
	MQ	1 day/150°C (302°F)	-	-	-	15
PMQ	-		-	-	25	
10W-30 Motor Oil (Texaco)	FVMQ	15 days/177°C(350°F)	-4	-33	-8	2
		30 days/177°C (350°F)	1	-52	-58	1
	50/50 VMQ/FVMQ	15 days/177°C (350°F)	-16	-35	10	9
		30 days/177°C (350°F)	-9	-76	-80	3
AMOCO Super Permalube 10W-30	VMQ	250 hr/150°C (302°F)	-18	-21	5	23
Sun 5W-30 SJ Auto Engine Oil	FVMQ (70 Durometer)	70 hours/150°C (302°F)	-1	1	0	0
		7 days/150°C (302°F)	1	-3	-6	0
Mobil 5W-30 HP Engine Oil	75% FVMQ 25% VMQ Blend.	3 days/150°C (302°F)	-9	-21	-15	12
		7 days/150°C (302°F)	-9	-26	-22	12

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

Automotive Oils and Fluids (Cont.)

Automobile Transmission Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Dynaflow Automatic Transmission Fluid	MQ	70 hr/93°C (200°F)	-15	-	-	15
	VMQ		-15	-	-	25
	PMQ		-10	-	-	35
GM Hydramatic Fluid (Type A)	VMQ	3 days/150°C (302°F)	-35	-40	-5	35
	FVMQ		-5	-10	-5	5
Socony Mobil Transmission Fluid (Type A)	MQ	1 day/121°C (250°F)	-10	-	-	35
	PMQ		-10	-	-	40
	MQ	7 days/121°C(250°F)	-10	-	-	35
Sun 109 Transmission Fluid	VMQ	100 hr/177°C (350°F)	-25	-40	nil	30
Texamatic A Transmission Fluid (Texaco)	VMQ	70 hr/65°C (150°F)	-10	-	-	10
	VMQ	70 hr/150°C (302°F)	-20	-30	-10	25
	PVMQ		-30	-85	-65	65
	FVMQ	nil	-25	-15	nil	
Texamatic C Transmission Fluid (Texaco)	VMQ	70 hr/177°C (350°F)	DT	DT	DT	DT
	MQ	1 day/121°C (250°F)	-10	-	-	35
	PMQ		-10	-	-	45
	MQ	7 days/121°C (250°F)	-20	-	-	40
VMQ	70 hr/150°C (302°F)	-25	-60	-25	25	
Texamatic TL 3528 Transmission Fluid (Texaco)	VMQ	70 hr/121°C (250°F)	-15	5	nil	25

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Automotive Oils and Fluids (Cont.)

Transmission and Differential Lubricants

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Hypoid EP Lubricant	FVMQ	14 days/149°C (300°F)	-20	nil	-10	nil
Mobilube GX-90 General Lubricant	VMQ	3 days/149°C(300°F)	DT	DT	DT	DT
	FVMQ		DT	DT	DT	DT
Swan Finch EP90 Lubricant	FVMQ	3 days/121°C (250°F)	-10	-70	nil	-10
		3 days/150°C (302°F)	DT	DT	DT	DT
TL 3450 Lubricant	VMQ	3 days/100°C (212°F)	-10	-	-	15
	VMQ	3 days/121°C (250°F)	-10	-60	-45	10
	FVMQ		-5	-5	-5	5
	VMQ	3 days/150°C (302°F)	DT	DT	DT	DT
FVMQ	DT		DT	DT	DT	

Shock Absorber Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Delco Shock Absorber Fluid	PMQ	3 days/71°C (160°F)	-	-	-	65
Standard Oil Shock Absorber Fluid	MQ	1 hr/150°C (302°F)	-15	-	-	25
	VMQ		-20	-	-	35
	MQ	1 hr/177°C (350°F)	-15	-	-	30
	VMQ		-20	-	-	45

Brake Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Wagner 21B Brake Fluid	MQ	7 days/24°C (75°F)	-5	-	-	5
	VMQ		0	-	-	5
	PVMQ		-5	-	-	5
	PVMQ	3 days/150°C (302°F)	-5	-90	-85	10
	FVMQ		DT	DT	DT	DT
		MQ	7 days/88°C(190°F)	-5	-	-
VMQ	-5	-		-	5	
PVMQ	-5	-		-	5	
Delco Supreme 550 Heavy-Duty Brake Fluid	VMQ	70 hr/150°C (302°F)	-4	-25	nil	4

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Fuels

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Diesel Fuel	MQ	7 days/24°C (75°F)	-25	-	-	85
	VMQ		-25	-	-	100
	PVMQ		-35	-	-	130
	MQ	7 days/54°C (130°F)	-25	-	-	90
	VMQ		-30	-	-	105
	PVMQ		-40	-	-	140
Gasoline	VMQ	5 min/24°C (75°F)	-	-	-	25
	PVMQ		-	-	-	20
	VMQ	30 min/24°C (75°F)	-	-	-	60
	PVMQ		-	-	-	75
	MQ	18 hr/24°C (75°F)	-25	-	-	245
Gasoline -Regular	FVMQ	24 hr/25°C (77°F)	-12	-39	-30	21
Gasoline -Low Lead	FVMQ	24 hr/25°C (77°F)	-12	-41	-30	20
White Gasoline Vapors	PMQ	14 days/24°C (75°F)	-10	-	-	50
	VMQ	7 days/24°C (75°F)	-20	-	-	165
JP-4 Fuel (MIL-J-5624F)	FVMQ	1 day/-54°C (-65°F)	-5	-10	nil	nil
	PVMQ	10 min/24°C (75°F)	-10	-	-	30
	PVMQ	1 day/24°C (75°F)	-	-	-	105
	FVMQ		-5	-20	-50	10
	FVMQ	3 days/24°C (75°F)	-5	-35	-20	10
	PVMQ	7 days/24°C (75°F)	-25	-75	-60	330
	FVMQ		-5	-20	-50	10
	FVMQ	14 days/24°C (75°F)	-5	-20	-50	10
		21 days/24°C (75°F)	-5	-30	-55	10
		30 days/24°C (75°F)	-5	-30	-55	10
		3 days/115°C (240°F)	-5	-55	-40	15
	15 days/121°C (250°F)	-20	-65	-40	20	
	3 days/177°C(350°F)	-25	-65	-20	25	
	3 days/200°C (392°F)	-35	-80	-10	30	
	3 days/232°C (450°F)	-45	-90	-20	20	
JP-5 Fuel (MIL-J-5624F)	FVMQ	7 days/24°C (75°F)	-5	-15	nil	5
JP-5 Fuel Jet Engine Oil	75% FVMQ 25% VMQ Blend.	22 hours/24°C (75°F)	-11	-45	-37	21
JP-8 Fuel	FVMQ	1 day/24°C (75°F)	-9	-8	0	3.7
		7 days/24°C (75°F)	-9	-13	-6	4.6
JP-8Jet Engine Fuel	FVMQ (75 Durometer)	7 days/163°C (325°F)	-11	0	-8	12
		28 days/163°C (325°F)	-18	-73	-38	14
Manufactured Gas (24% Methane, 3% Ethane, 18% Carbon Monoxide, 55% Hydrogen)	FVMQ	2 mo/121°C (250°F)	GR	GR	GR	GR

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

GR - good resistance

Fuels (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Gasohol 10%; Methanol/ 90%; No Lead Gasoline	FVMQ	1 day/24°C (75°F)	-19	-47	-35	27.5
		7 days/24°C (75°F)	-19	-19	-26	25.9
		14 days/24°C (75°F)	-20	-48	-26	26.6
		28 days/24°C (75°F)	-21	-50	-26	24.4
Gasohol 10%; Ethanol/90%;	FVMQ	1 day/24°C (75°F)	-18	-37	-19	21.5
		7 days/24°C (75°F)	-16	-37	-16	21.3
Unsymmetrical Dimethyl Hydrazine	VMQ	4 days/24°C (75°F)	nil	-25	-50	60
	FVMQ		DT	DT	DT	DT

Hydraulic Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Aerosafe 2300 (Stauffer)	VMQ	70 hr/25°C (77°F)	-12	-26	-17	21
	VMQ	70 hr/70°C (158°F)	-15	-36	-5	22
	FVMQ		-49	-97	-62	18
Exxon WS2406 Fluid	MQ	7 days/71°C(160°F)	-15	-	-	15
	VMQ		-10	-	-	20
	FVMQ		-20	-	-	35
	MQ	1 day/121°C (250°F)	-5	-	-	20
	VMQ		-10	-	-	35
	PMQ		-5	-	-	45
	MQ	1 hr/177°C (350°F)	-10	-	-	15
	VMQ		-10	-	-	20
	PMQ		-15	-	-	30
Hydrolube H-2 Fluid	MQ	70 hr/24°C (75°F)	-5	-15	10	5
	VMQ		-5	nil	15	5
	PVMQ		-5	-15	-10	5
	MQ	5 days/24°C (75°F)	-5	-	-	5
	PMQ		-10	-	-	10
	MQ	14 days/24°C (75°F)	-5	-	-	10
	PMQ		-10	-	-	15
	MQ	27 days/24°C (75°F)	-5	-	-	10
	PMQ		-10	-	-	15
	MQ	5 days/65°C (150°F)	-10	-	-	10
	PMQ		-10	-	-	20
	MQ	24 days/65°C (150°F)	-5	-	-	15
	PMQ		-10	-	-	20
	MQ	7 days/70°C (158°F)	-10	-10	20	5
	VMQ		-10	-	-	5
PVMQ		-5	-15	-10	5	
Oronite M2V (Chevron)	VMQ	7 days/100°C (212°F)	-19	-57	-62	73
	FVMQ		-3	nil	-16	2
	VMQ	7 days/150°C (302°F)	-24	-70	-63	96
	FVMQ		nil	-22	-12	4
	VMQ	7 days/177°C (350°F)	-35	-86	-77	130
	FVMQ		-4	-34	-38	5

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Hydraulic Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Oronite 8200 Fluid (Chevron)	FVMQ	3 days/177°C(350°F)	-15	-10	-10	5
Oronite 8515 Fluid (Chevron)	FVMQ	1 day/-54°C (-65°F)	nil	5	5	nil
	MQ	3 days/24°C (75°F)	-15	-	-	40
	VMQ		-20	-	-	45
	PVMQ		-15	-	-	40
	MQ	3 days/130°C (265°F)	-20	-	-	60
	VMQ		-30	-	-	80
	PVMQ		-25	-	-	115
	FVMQ	3 days/150°C(302°F)	-5	-10	-10	5
		3 days/177°C (350°F)	-10	-40	-5	10
		3 days/200°C (392°F)	-45	-95	-40	15
Oronite Hyjet (Chevron)	FVMQ	70 hr/70°C(158°F)	-25	-79	59	24
	VMQ		-10	-4	9	9
Pydraul 60 Fluid	VMQ	3 days/24°C (75°F)	-5	-	-	5
	PVMQ		-10	-	-	5
	FVMQ		-5	-	-	5
	VMQ	3 days/121°C (250°F)	-10	-	-	10
	PVMQ		-25	-	-	10
	FVMQ		-15	-	-	5
Pydraul A-200 Fluid	VMQ	3 days/24°C (75°F)	-5	-	-	5
	PVMQ		-10	-	-	5
	FVMQ		-5	-	-	nil
	VMQ	3 days/121°C (250°F)	-10	-	-	10
	PVMQ		-10	-	-	15
	FVMQ		-5	-	-	5
	VMQ	1 day/177°C (350°F)	-5	-	-	15
	PVMQ		-10	-	-	120
	FVMQ		-5	-	-	5
Pydraul F9 Fluid	MQ	3 days/24°C (75°F)	-5	-15	nil	5
	VMQ		-5	-	-	5
	PMQ		-10	-	-	10
	PVMQ		-10	nil	5	5
	MQ	3 days/150°C (302°F)	-5	-15	-5	10
	VMQ		-5	nil	10	10
	PMQ		-10	-	-	15
	PVMQ		-10	nil	-5	15
	FVMQ		-5	-5	5	5
	FVMQ	3 days/177°C (350°F)	-10	-60	-15	-10
Pydraul 150	FVMQ	7 days/150°C (302°F)	DT	DT	DT	DT
Skydrol 500B (Monsanto)	VMQ	70 hr/70°C (158°F)	-9	-17	3	10
	PVMQ		-15	-24	-11	19
Skydrol HT (Monsanto)	VMQ	70 hr/70°C (158°F)	-13	-23	-8	20
	PVMQ		-24	-50	-32	40

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Hydraulic Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Skydrol LD (Monsanto)	VMQ	70 hr/70°C (158°F)	-16	-22	-3	26
	FVMQ		-37	-87	-71	108
Skydrol LD-4 (Monsanto)	FVMQ	1 day/24°C (75°F)	-24	-82	-68	68
		1 day/70°C (158°F)	-29	-85	-73	87
Skydrol 7000 Fluid (Monsanto)	MQ	3 days/24°C (75°F)	-5	-10	-5	5
	VMQ		nil	-5	-5	5
	PVMQ		-10	-10	-5	10
	MQ	14 days/24°C (75°F)	nil	-	-	5
	PMQ		-10	-	-	5
	MQ	3 days/93°C (200°F)	-5	-10	nil	5
VMQ	-5		-10	-10	5	
PVMQ	-10		-15	-10	10	

Transformer and Instrument Oils

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Askerol Transformer Oil (Monsanto) - Chlorinated	VMQ	35 days/24°C (75°F)	nil	-20	-15	10
		44 days/24°C (75°F)	-5	-10	-15	10
		60 days/24°C (75°F)	-5	-10	-15	10
		7 days/70°C (158°F)	-5	-10	-20	10
		14 days/70°C (158°F)	-5	-20	-20	15
		28 days/70°C (158°F)	-5	-15	-15	10
		38 days/70°C (158°F)	-5	-15	-15	15
		1 day/121°C (250°F)	-5	-15	-15	20
		3 days/121°C (250°F)	-5	-15	-15	20
		7 days/121°C (250°F)	-10	-15	-15	15
14 days/121°C (250°F)	-5	-10	-15	20		
Inerteen Transformer Oil (Westinghouse) - Chlorinated	MQ	3 days/24°C (75°F)	-5	-10	-5	10
	VMQ		-5	-10	-5	10
	PVMQ		-10	-15	-15	15
	MQ	3 days/115°C (240°F)	-10	-25	-5	15
	PVMQ		-10	-25	-10	15
	FVMQ		nil	-15	nil	5
VMQ	3 days/177°C (350°F)	-15	-25	-15	30	
N-43 Fluorocarbon Capacitor Fluid	VMQ	3 days/150°C (302°F)	-5	-	-	5
	PVMQ		nil	-	-	5
Pyranol Transformer Oil (General Electric) - Chlorinated	PMQ	7 days/100°C (212°F)	-10	-	-	25
RCA-Gulf Instrument Oil A	VMQ	3 days/93°C (200°F)	-20	-	-	70
	PVMQ		-30	-	-	5
Univolt 35 Transformer Oil	MQ	3 days/150°C(302°F)	-15	-25	-20	40
	VMQ		-15	-45	-45	50
	PVMQ		-30	-30	-15	55
	FVMQ		nil	-10	nil	5

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

Transformer and Instrument Oils (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Wemco C Transformer Oil	MQ	3 days/24°C (75°F)	-15	-	-	35
	VMQ		-20	-	-	40
	PVMQ		-30	-	-	45
	VMQ	1 yr/79°C (175°F)	-35	-	-	40
	VMQ	3 days/177°C(350°F)	-55	-	-	140
	FVMQ		-5	20	5	10
Coolanol 35 (Monsanto)	VMQ	3 days/121°C (250°F)	-21	-67	-68	101
	FVMQ		1	1	-10	3
Coolanol 45 (Monsanto)	FVMQ	70 hr/177°C(350°F)	-3	-12	-14	4

Speciality Oils, Greases and Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
ANG 15 Industrial Grease (Texaco Regal Starfak Special)	MQ	3 days/24°C (75°F)	-5	nil	nil	10
	VMQ		-10	nil	nil	10
	MQ	3 days/150°C (302°F)	-10	nil	nil	20
	VMQ		-15	nil	nil	20
ANG 25 Diester Base (Texaco TG-749)	VMQ	3 days/25°C (77°F)	-5	-	-	15
ANG 25 Diester Base (Texaco TG-749)	PMQ	3 days/93°C (200°F)	-15	-	-	30
		1 day/150°C (302°F)	-20	-	-	40
		7 days/ 150°C (302°F)	TB	TB	TB	TB
ANG 25 Glycerol Ester (Texaco)	PMQ	1 day/71°C (160°F)	-10	-	-	10
ANO No. 3 Grade M; Extreme Pressure (GAF Corp.)	MQ	3 days/177°C (350°F)	-	-	-	45
	PMQ		-	-	-	30
ANO No. 6 Oil (GAF Corp.)	MQ	1 day/24°C (75°F)	-10	-	-	30
	PMQ		-10	-	-	45
	MQ	7 days/24°C (75°F)	-15	-	-	35
	PMQ		-20	-	-	60
	MQ	1 day/150°C (302°F)	-25	-	-	95
	PMQ		-25	-	-	145
ANO No. 9 Oil (GAF Corp.)	MQ	1 day/121°C (250°F)	-10	-	-	35
	PMQ		-15	-	-	40
	MQ	3 days/121°C (250°F)	-15	-	-	45
	PMQ		-20	-	-	70
	MQ	7 days/121°C(250°F)	-15	-	-	45
	PMQ		-20	-	-	65
ANO No. 11 Oil (GAF Corp.)	MQ	1 day/121°C (250°F)	-5	-	-	10
	PMQ		-15	-	-	20
	MQ	3 days/121°C (250°F)	-10	-	-	15
	PMQ		-15	-	-	25
	MQ	7 days/121°C (250°F)	-10	-	-	15
	PMQ		-15	-	-	25
ANO No. 366 Oil (GAF Corp.)	MQ	3 days/93°C (200°F)	-20	-	-	95
	PMQ		-10	-	-	140

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

TB - too brittle to test

Speciality Oils, Greases and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Aroclor 1254 (Monsanto)	VMQ	3 days/24°C (75°F)	-5	10	5	5
		3 days/150°C(302°F)	-10	-5	nil	10
Cosmoline 2046 (Fritzsche, Dodge & Olcutt)	VMQ	4 days/24°C (75°F)	-35	-	-	55
Crude Oil 7 API	FVMQ	14 days/24°C (75°F)	-	-	-	5
	VMQ	3 days/83°C (180°F)	-10	-	-	25
	FVMQ	14 days/83°C (180°F)	-	-	-	5
		14 days/135°C (275°F)	-10	-	-	5
Crude Oil 315 API	VMQ	14 days/24°C (75°F)	-	-	-	10
		3 days/83°C (180°F)	-20	-	-	60
	FVMQ	14 days/83°C (180°F)	-	-	-	5
		14 days/135°C (275°F)	-5	-70	-45	-2
Delco No. 9	PVMQ	1 day/100°C (212°F)	-15	-15	15	10
	VMQ	5 days/100°C (212°F)	-10	-	-	10
	PVMQ		-15	-	-	10
Delco No. 11	MQ	5 days/100°C (212°F)	-5	-	-	5
	VMQ		-5	-	-	5
Dowtherm A Heat Transfer Oil (Dow)	VMQ	3 days/24°C (75°F)	-10	-	-	10
		3 days/177°C (350°F)	-30	-	-	40
FC-75 Fluorochemical Fluid (3M)	VMQ	1 day/24°C (75°F)	-5	-	-	nil
	PVMQ		-5	-	-	nil
	FVMQ		5	-	-	nil
	VMQ	7 days/65°C (150°F)	nil	-	-	5
	PVMQ		-5	-	-	5
	FVMQ		nil	-	-	5
Gas Drip Oil	VMQ	3 days/24°C (75°F)	-25	-	-	250
	PVMQ		-30	-	-	500
	FVMQ		-5	-	-	20
GE Transil Oil	VMQ	3 days/24°C (75°F)	-20	-	-	35
		3 days/93°C (200°F)	-30	-	-	50
GM 14X Heavy Duty Oil	VMQ	5 days/100°C (212°F)	-5	-	-	5
Mineral Oil	VMQ	3 days/24°C (75°F)	-10	-30	-10	25
	PVMQ		-15	-20	-10	35
Mineral Oil (Shell No. 5)	VMQ	3 days/121°C (250°F)	-20	-55	-35	60
	PVMQ		-35	-55	-20	75
	MQ	1 day/100°C (212°F)	-10	-	-	25
	PMQ		-5	-	-	40
	MQ	1 day/121°C (250°F)	-15	-	-	25
	PMQ		-10	-	-	40
	MQ	1 day/149°C (300°F)	-15	-	-	30
PMQ		-10	-	-	55	

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

Speciality Oils, Greases and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Navy Crankcase Oil No. 2135	VMQ	4 days/93°C (200°F)	-15	-	-	10
Navy Crankcase Oil No. 9250	VMQ	4 days/93°C (200°F)	-10	-	-	10
Pacemaker Fluid 100T	VMQ	1 day/177°C (350°F)	-25	-	-	50
	PVMQ		-35	-	-	60
	VMQ	3 days/177°C (350°F)	-30	-	-	55
	PVMQ FVMQ		-40 -5	- -20	- -10	65 5
PRL 3313 (Rohm and Haas)	MQ	1 day/71°C (160°F)	-15	-	-	15
	VMQ		-15	-	-	15
	PMQ		-20	-	-	30
	MQ	3 days/71°C (160°F)	DT	DT	DT	DT
	PMQ		DT	DT	DT	DT
	MQ	1 day/121°C (250°F)	DT	DT	DT	DT
SG 4766 Glycol Ester Base Grease (Standard Oil)	MQ	70 hr/24°C (75°F)	-10	-	-	5
	PMQ		-10	-	-	10
	MQ	3 days/24°C (75°F)	-10	-	-	10
	PMQ		-10	-	-	15
	PMQ	1 day/71°C (160°F) 3 days/71°C (160°F)	-10 -10	- -	- -	10 10
Shell Aircraft Turbine Lubricant A	FVMQ	70 hr/150°C (302°F) 140 hr/150°C(302°F)	-5 -11	-9 -24	-25 -32	8 10
	FVMQ	70 hr/150°C (302°F) 140 hr/150°C (302°F)	-3 -8	-26 -71	-50 -69	6 7
Shell B & B Grease	VMQ	70 hr/74°C (165°F) 912 hr/74°C (165°F)	-15 -16	-34 -9	-10 -20	26 26
	PMQ	70 hr/74°C (165°F) 912 hr/74°C (165°F)	-17 -19	-11 -15	-7 -13	30 30
	PMQ	1 day/150°C (302°F) 6days/150°C (302°F)	-15 -20	- -	- -	50 50
Socony Mobil RL 147-A No. 7	PMQ	1 day/150°C (302°F) 6days/150°C (302°F)	-15 -20	- -	- -	50 50
	PMQ	1 day/150°C (302°F) 6days/150°C (302°F)	-25 -45	- -	- -	70 55
Tectyl 502C Rust Inhibitor	MQ	14 days/24°C (75°F)	-5	5	5	nil
Tectyl 511-M Rust Inhibitor	MQ	14 days/24°C (75°F)	nil	5	-5	nil
Texas 1500 Oil (HD Concentrate)	MQ	10 days/150°C (302°F) 21 days/150°C (302°F)	-15 -20	-20 -30	-20 -10	10 10

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Speciality Oils, Greases and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %	
Tricresyl Phosphate	MQ	3 days/24°C (75°F)	nil	nil	-5	nil	
	VMQ		nil	-5	5	nil	
	PVMQ		nil	-5	-5	nil	
		MQ	3 days/177°C (350°F)	nil	-40	-40	5
		VMQ		-5	-25	-10	5
		PVMQ		nil	-45	-50	5
		VMQ	3 days/200°C (392°F)	DT	DT	DT	DT
	Turbo Oil No. 35	PVMQ	7 days/24°C (75°F)	-15	-35	-20	15
			7 days/65°C (150°F)	-20	-35	-25	15
VMQ		3 days/71°C (160°F)	-10	-10	-15	10	
PMQ			-15	-35	-25	15	
		VMQ	3 days/121°C (250°F)	-15	-10	-15	10
		PMQ		-15	-35	-20	15
	FVMQ	3 days/150°C (302°F)	-10	-30	25	10	
Ucon Lubricant LB1145 (gear oil) (Union Carbide)	MQ	3 days/150°C (302°F)	nil	-	-	nil	
	VMQ		nil	-	-	nil	
	PMQ		nil	-	-	nil	
Ucon Water-Soluble Lubricant 50-HB-55 (Union Carbide)	MQ	3 days/150°C (302°F)	-5	-	-	nil	
	VMQ		-5	-	-	nil	
	PMQ		nil	-	-	nil	
Ucon Lubricant 50-HB-100 (Union Carbide)	MQ	3 days/150°C (302°F)	nil	-	-	nil	
	VMQ		-5	-	-	nil	
	PMQ		nil	-	-	nil	
Ucon Lubricant 50-HB-260 (Union Carbide)	MQ	3 days/150°C (302°F)	nil	-	-	nil	
	VMQ		nil	-	-	nil	
	PMQ		nil	-	-	nil	
Ucon Lubricant 50-HB-280-X (Union Carbide)	MQ	3 days/150°C (302°F)	-5	-	-	nil	
	VMQ		-5	-	-	nil	
Ucon Lubricant 50-HB-660 (Union Carbide)	MQ	3 days/150°C (302°F)	nil	-	-	nil	
	VMQ		nil	-	-	nil	
	PMQ		nil	-	-	nil	
Ucon Lubricant 50-HB-5100 (Union Carbide)	MQ	3 days/150°C (302°F)	nil	-	-	nil	
	VMQ		nil	-	-	nil	
	PMQ		nil	-	-	nil	

Solvents

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Acetone	MQ	7 days/24°C (75°F)	-10	-	-	25
	VMQ		-10	-	-	15
	PVMQ		-10	-	-	20
	FVMQ		-20	-85	-75	180
Benzene	VMQ	14 days/24°C (75°F)	-	-	-	175
	FVMQ		-17	-22	-15	23
	FVMQ	3 days/70°C (158°F)	-10	-50	-40	20

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Solvents (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Butyl Acetate	VMQ	7 days/24°C (75°F)	-30	-	-	150
	PMQ		nil	-	-	150
	PVMQ		-25	-	-	125
Butyl Alcohol (Butanol)	MQ	7 days/24°C (75°F)	-10	-	-	20
	VMQ		-10	-	-	15
	PMQ		-15	-	-	40
	PVMQ		-10	-	-	35
	FVMQ		nil	-	-	10
Carbon Tetrachloride	VMQ	7 days/24°C (75°F)	-20	-	-	165
	PVMQ		-10	-	-	165
	FVMQ		-5	-45	-30	20
	FVMQ	5 days/49°C (120°F)	-10	-	-	20
Chlorobromomethane	FVMQ	7 days/24°C (75°F)	-10	-45	-50	25
	MQ	2 days/67°C (153°F)	-20	-	-	70
	VMQ		-20	-	-	95
	PVMQ		-25	-	-	235
Chloroform	FVMQ	5 days/24°C (75°F)	-10	nil	nil	30
Chlorothene Solvent (Dow)	FVMQ	1 day/24°C (75°F)	-15	-	-	50
	VMQ	7 days/24°C (75°F)	-	-	-	245
Cyclohexane	FVMQ	2 days/24°C (75°F)	-	-	-	15
	VMQ	7 days/24°C (75°F)	-	-	-	250
Diacetone Alcohol	VMQ	5 days/24°C (75°F)	-5	-	-	5
Dichloroisopropyl Ether	PMQ	7 days/24°C (75°F)	-	-	-	nil
Diethyl Ether	FVMQ	7 days/24°C (75°F)	-10	-40	-45	50
Ethyl Alcohol	MQ	7 days/24°C (75°F)	-5	-	-	nil
	VMQ		-5	-	-	5
	PVMQ		-10	-	-	20
	FVMQ		nil	-30	-15	5
Ethylenedichloride	FVMQ	3 days/24°C (75°F)	-10	-	-	50
	VMQ	7 days/24°C (75°F)	-	-	-	45
Heptane	FVMQ	7 days/60°C (140°F)	-10	-30	-30	25
Isopropyl Alcohol	PMQ	7 days/24°C (75°F)	-10	-	-	10
Methyl Alcohol	MQ	7 days/24°C (75°F)	nil	nil	nil	nil
Methyl Chloride	FVMQ	14 days/25°C (77°F)	-12	-34	-11	4
	MQ	7 days/24°C (75°F)	NR	NR	NR	NR
	VMQ		-15	-	-	150
	PVMQ		-15	-	-	150
Methylene Chloride	VMQ	72 hr/25°C (77°F)	-	-	-	180
	FVMQ		-	-	-	70
Mineral Spirits	FVMQ	30 days/24°C (75°F)	nil	nil	nil	nil
Monochlorobenzene	FVMQ	7 days/24°C (75°F)	-5	-45	-40	25

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

NR - not recommended

Solvents (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Naphtha	FVMQ	3 days/24°C (75°F)	-	-	-	10
Nitrocellulose Solvent (Toluene, Ethyl Alcohol, Ethyl Acetate, Methyleneethylketone, Butyl Acetate)	VMQ	2 days/24°C (75°F)	-25	-	-	135
	PVMQ		-45	-	-	165
	FVMQ		-25	-	-	65
Ortho-Chloroethylbenzene	FVMQ	7 days/24°C (75°F)	-5	-55	-40	15
Ortho-Chlorotoluene	FVMQ	7 days/24°C (75°F)	-5	-45	-45	20
Oxylene Solvent	FVMQ	1 day/24°C (75°F)	-15	-	-	90
Perchloroethylene	FVMQ	3 days/24°C (75°F)	-10	-	-	10
	PMQ	14 days/24°C (75°F)	-10	-	-	45
	FVMQ	1 day/107°C (225°F)	-15	-	-	20
Propylenedichloride	FVMQ	5 days/49°C (120°F)	-10	-	-	55
Solvatone Solvent (Union Carbide)	VMQ	1 day/24°C (75°F)	-15	-	-	30
Stoddard Solvent	MQ	7 days/24°C (75°F)	NR	NR	NR	NR
	VMQ		-20	-	-	160
	PVMQ		-15	-	-	150
Toluene	MQ	7 days/24°C (75°F)	NR	NR	NR	NR
	VMQ		-	-	-	205
	PVMQ		-20	-	-	150
	FVMQ		-10	-50	-35	20
Toluene Vapor	PMQ	14 days/24°C (75°F)	-10	-	-	50
Turpentine	VMQ	16 hr/24°C (75°F)	-	-	-	230
	FVMQ		-	-	-	15
Xylene (Xylol)	VMQ	15 min/24°C (75°F)	-20	-	-	40
		30 min/24°C (75°F)	-25	-	-	45
		1 hr/24°C (75°F)	-30	-	-	60
		2 hr/24°C (75°F)	-30	-	-	80
		5 days/24°C (75°F)	-35	-	-	135
	FVMQ	3 days/24°C (75°F)	-10	-45	-35	20
		7 days/24°C (75°F)	-10	-55	-40	20

Silicone Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
XIAMETER® PMX-200 Silicone Fluid, 0.65 centistokes	FVMQ	3 days/24°C (75°F)	-5	-45	-30	5
		1 day/100°C (212°F)	-5	-	-	15
		3 days/150°C (302°F)	-10	-60	-30	25
XIAMETER® PMX-200 Silicone Fluid, 3 centistokes	FVMQ	3 days/24°C (75°F)	nil	-15	-10	nil
		3 days/150°C (302°F)	-10	-30	-10	10
XIAMETER® PMX-200 Silicone Fluid, 10 centistokes	FVMQ (40 Durometer)	3 days/23°C (73°F)	-1	-5	3	0
		14 days/23°C (73°F)	-2	-9	0	0
		3 days/100°C (212°F)	-3	-4	3	1
		14 days/100°C (212°F)	-1	-6	0	1
XIAMETER® PMX-200 Silicone Fluid, 100 centistokes	FVMQ (40 Durometer)	3 days/23°C (73°F)	-3	3	7	0
		14 days/23°C (73°F)	-4	1	5	0
		3 days/100°C (212°F)	-4	6	10	0
		14 days/100°C (212°F)	-3	5	10	0

MQ - methyl groups only
V - vinyl groups

P - phenyl groups

F - fluorine-containing groups

NR - not recommended

Silicone Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
XIAMETER® PMX-200 Silicone Fluid, 1000 centistokes	FVMQ (40 Durometer)	3 days/23°C (73°F)	-3	3	4	0
		14 days /23°C (73°F)	-4	1	2	0
		3 days/100°C (212°F)	-5	-2	0	1
		14 days/100°C (212°F)	-2	0	5	0
XIAMETER® PMX-200 Silicone Fluid, 60000 centistokes	VMQ PMQ FVMQ	1 day 24°C (75°F)	-5	-10	nil	5
		3 days/24°C (75°F)	-5	-10	-10	5
			nil	-10	nil	nil
	PMQ FVMQ	3 days/24°C (75°F)	-5	-15	-5	5
			nil	-10	-15	nil
		VMQ PMQ FVMQ	7 days/24°C (75°F)	-5	-10	nil
	VMQ PMQ FVMQ	7 days/24°C (75°F)	-10	-5	-5	10
			nil	-5	nil	nil
		VMQ PMQ FVMQ	1 day 150°C (302°F)	-5	-15	-10
	VMQ PMQ FVMQ	1 day 150°C (302°F)	-10	-5	nil	10
			-5	-15	-5	nil
		VMQ PMQ FVMQ	3 days/150°C (302°F)	-10	-15	-10
VMQ PMQ FVMQ	3 days/150°C (302°F)	-10	-15	-10	10	
		-5	-25	nil	nil	
	VMQ PMQ FVMQ	7 days/150°C (302°F)	-10	-30	-20	15
VMQ PMQ FVMQ	7 days/150°C (302°F)	-10	nil	-25	15	
		-5	-25	-15	nil	
	XIAMETER® RSN-0220 Flake Resin	FVMQ	2 days/150°C (302°F)	nil	-	-
Dow Corning® 510 Fluid	MQ VMQ PVMQ	3 days/24°C (75°F)	-15	-	-	40
		3 days/24°C (75°F)	-15	-	-	35
			-20	-	-	35
	VMQ	1 day/150°C (302°F)	-20	-	-	35
	MQ VMQ PVMQ FVMQ	3 days/150°C (302°F)	-20	-	-	40
			-25	-	-	45
			-30	-	-	50
			nil	-10	-15	nil
Dow Corning® 550 Fluid	MQ VMQ PVMQ	3 days/24°C (75°F)	-5	-	-	5
		3 days/24°C (75°F)	-5	-	-	10
			-10	-	-	10
	MQ VMQ PVMQ FVMQ	3 days/150°C (302°F)	-10	-	-	10
			-10	-	-	10
			-10	-	-	10
			nil	-3	-15	nil
VMQ	7 days/150°C (302°F)	-	-	-	10	

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

NE - no effect

Silicone Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Dow Corning® 702 Diffusion Pump Fluid	VMQ	1 day/150°C (302°F)	-25	-	-	60
Dow Corning® 710 Fluid	FVMQ	3 days/150°C (302°F)	nil	nil	-15	nil
	VMQ	7 days/150°C (302°F)	-5	-	-	5
		7 days/150°C (302°F)	-10	-	-	5
		7 days/200°C (392°F)	-10	-	-	10
Dow Corning® 710 Fluid	MQ	3 days/24°C (75°F)	-5	-	-	nil
	VMQ		-5	-	-	5
	PVMQ		-5	-	-	5
	MQ	3 days/150°C (302°F)	-10	-	-	5
	VMQ		-5	-	-	5
	PVMQ		-10	-	-	10
		FVMQ	14 days/200°C (392°F)	-20	-70	10
Dow Corning® FS-1265 Fluid	VMQ	7 days/150°C (302°F)	nil	10	-5	nil
	FVMQ		-20	-55	-45	80
	PVMQ		-5	15	-10	5

Silicone Compounds and Greases

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %	
Dow Corning® 4 Compound	PMQ	1 day/24°C (75°F)	-5	-	-	5	
		3 days/24°C (75°F)	-5	-	-	10	
		7 days/24°C (75°F)	-5	-	-	20	
	MQ VMQ PMQ	1 day/150°C (302°F)		-20	-	-	25
				-15	-	-	25
				-5	-	-	15
	VMQ PMQ	3 days/150°C (302°F)		-	-	-	25
				-10	-	-	25
	VMQ PMQ	7 days/150°C (302°F)		-	-	-	30
				-10	-	-	30
	PMQ	1 day/200°C (392°F) 3 days/200°C (392°F) 7 days/200°C (392°F)		-10	-	-	20
				-20	-	-	30
			-30	-	-	40	
Dow Corning® 5 Compound	MQ	1 day/150°C (302°F)	-20	-	-	20	
	VMQ		-15	-	-	15	
Molykote® 33 Grease	FVMQ	3 days/25°C (77°F)	-5	-	-	4	
		3 days/177°C (350°F)	-11	-	-	9	

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

Silicone Compounds and Greases (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Molykote® 44L Grease	VMQ	7 days 150°C (302°F)	-	-	-	15
Molykote® 55 Pneumatic Grease	PMQ	3 days/93 °C (200 °F) 3 days /250°C (482°F)	-15 DT	- DT	- DT	60 DT
	VMQ	3 days/177°C (350°F)	DT	DT	DT	DT
	FVMQ	3 days/25°C (77°F) 3 days/177°C (350°F)	-5 -11	- -	- -	4 9
Dow Corning® 340 Heat Sink Compound	VMQ	70 hr/150°C (302°F)	-9			11
Molykote® FS-1292 Grease	75/25 VMQ/FVMQ	70 hr/177°C(350°F)	-6	-11	-28	6
	50/50 VMQ/FVMQ	70 hr/177°C (350°F)	-17	1	-6	16

Food Products

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Beer	VMQ	22 hr/70°C (158°F)	nil			nil
	FVMQ		-5	-	-	nil
Butter (liquid)	VMQ	22 hr/70°C(158°F)	-5	-	-	nil
	FVMQ		-3	-	-	nil
Coca-Cola Syrup	VMQ	1 day/24°C (75°F)	nil	nil	nil	nil
	PVMQ		nil	10	15	nil
	FVMQ		5	nil	5	nil
	VMQ	28 days/24°C (75°F)	nil	-10	-10	nil
	PVMQ		nil	20	20	nil
	FVMQ		nil	nil	10	nil
Coffee	VMQ	7 days/83°C(180°F) 14 days/83°C (180° F)	-5 -5	-15 -5	nil nil	nil 5
	VMQ (High Strength)	1 day/200°C (392°F)	nil	-35	-40	5
		3 days/200°C (392°F)	-5	-80	-75	5
7 days/200°C (392°F)		BR	BR	BR	BR	
Lard	VMQ	7 days/200°C (392°F) 1 hr/260°C (500°F)	nil -10	-30 -25	-35 -20	nil 5
	VMQ	7 days/150°C (302°F)	-5	-15	-10	nil
Mazola Oil	VMQ	7 days/150°C (302°F)	-5	-15	-10	nil
Orange Peel Oil	VMQ	1 day/24°C (75°F)	-	-	-	-100

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
BR - brittle

Food Products (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %	
Orange Syrup	VMQ	1 day/24°C (75°F)	nil	nil	5	nil	
	PVMQ		nil	5	10	nil	
	FVMQ		nil	-15	5	5	
	VMQ	28 days/24°C (75°F)	nil	-5	-5	nil	
			PVMQ	nil	15	25	nil
			FVMQ	-5	-15	5	nil
	VMQ	60 days/24°C (75°F)	nil	-5	-10	nil	
			PVMQ	nil	nil	5	nil
			FVMQ	-5	-35	-15	5
Scotch Whisky	VMQ	1 day/24°C (75°F)	nil	nil	-5	nil	
	PVMQ		nil	nil	5	nil	
	FVMQ		nil	-15	3	5	
	VMQ	28 days/24°C (75°F)	nil	-5	10	nil	
			PVMQ	nil	5	20	nil
			FVMQ	-5	-15	15	nil
	VMQ	60 days/24°C (75°F)	nil	-10	5	nil	
			PVMQ	nil	-10	-5	5
			FVMQ	-5	-35	-15	3
Spry Shortening	VMQ	7 days/150°C (302°F)	-5	-15	-15	nil	
Tab Concentrate	VMQ	1 day/24°C (75°F)	nil	nil	5	nil	
	PVMQ		nil	nil	3	nil	
	FVMQ		nil	-5	3	nil	
	VMQ	28 days/24°C (75°F)	nil	5	30	nil	
			PVMQ	nil	5	10	nil
			FVMQ	nil	nil	10	nil
	VMQ	60 days/24°C (75°F)	nil	nil	-10	nil	
			PVMQ	nil	-5	-5	nil
			FVMQ	nil	-10	-5	nil
Tia Maria Liquor	VMQ	1 day/24°C (75°F)	nil	nil	5	nil	
	PVMQ		nil	10	10	nil	
	FVMQ		nil	-10	3	nil	
	VMQ	28 days/24°C (75°F)	nil	nil	10	nil	
			PVMQ	nil	10	10	nil
			FVMQ	-5	-15	20	nil
	VMQ	60 days/24°C (75°F)	nil	-5	-5	nil	
			PVMQ	nil	-5	nil	nil
			FVMQ	-5	-25	-5	nil
Vegetable Oil (Kraft)	VMQ (High Strength)	1 day/200°C (392°F)	-5	-30	-25	5	
		3 days/200°C (392°F)	nil	-40	-45	5	
		7 days/200°C (392°F)	-5	-80	-75	5	
Vinegar	VMQ (High Strength)	1 day/24°C (75°F)	nil	-5	nil	nil	
		7 days/24°C (75°F)	nil	-5	nil	nil	

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

Water and Steam

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %	
Water	MQ VMQ PVMQ	7 days/24°C (75°F)	nil nil nil	-5 - -5	-5 - -10	5 nil nil	
	MQ VMQ PVMQ	7 days/70°C (158°F)	-5 nil -5	-5 -5 -10	5 10 -5	5 nil nil	
	VMQ PVMQ FVMQ	3 days/100°C (212°F)	-5 -3 nil	-5 -5 -	-15 -5 -	nil nil nil	
	MQ VMQ	7 days/100°C (212°F)	-5 nil	-20 -	20 -	nil 5	
	VMQ	14 days/100°C (212°F)	nil	-	-	5	
	MQ	1 day/121°C (250°F) 3 days/121°C (250°F)	-5 -5	- -	- -	5 5	
	FVMQ	70 hr/150°C (302°F)	-5	-	-	nil	
	MQ	1 day/177°C (350°F) 3 days/177°C (350°F)	-15 DT	- DT	- DT	15 DT	
	Steam	MQ VMQ PVMQ	7 days/5 psi	-5 -5 -5	-25 -15 -10	5 5 10	nil 5 nil
		MQ VMQ PVMQ	14 days/5 psi	-5 -5 -5	-35 -30 -3	-10 -15 10	5 3 nil
		MQ VMQ PVMQ	7 days/10 psi	-5 -5 -5	-30 -30 -10	-10 -10 -10	5 5 nil
		MQ VMQ PVMQ	14 days/10 psi	-5 -5 -5	-35 -40 -10	-15 -20 -10	5 5 nil
		MQ VMQ PVMQ	7 days/20 psi	-5 -5 -5	-35 -35 -15	-15 20 -15	5 3 nil
MQ VMQ PVMQ		14 days/20 psi	-5 -5 -5	-45 -45 -20	-20 -40 -15	5 5 nil	
VMQ		1 day/50 psi 3 days/50 psi 5 days/50 psi 7 days/50 psi	-5 -5 -5 -5	-25 -30 -40 -65	-10 -5 -25 -30	5 5 5 5	

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Water and Steam (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Steam	VMQ	1 day/65 psi	-10	-30	-30	5
		3 days/65 psi	-5	-50	-25	5
		7 days/65 psi	-10	-65	-50	5
		1 day/80 psi	-10	-40	-10	5
		3 days/80 psi	-10	-60	-40	10
		7 days/80 psi	-10	-75	-45	5
	MQ	16 hr/100psi	-10	-30	25	nil
	MQ	1 day/100 psi	-10	-40	-10	5
	VMQ*		3	-11	-2	-2
	PVMQ		-5	-25	5	nil
	FVMQ		-5	-20	15	nil
	MQ	3 days/100 psi	-10	-60	-20	10
	VMQ		4	-25	-10	-4
	PVMQ		-10	-35	-5	nil
MQ	7 days/100 psi	-20	-30	-25	5	
VMQ		6	-35	-26	-6	
PVMQ		-20	-75	-75	nil	

Acids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Acetic Acid (5%)	VMQ	7 days/24°C (75°F)	-5	-	-	5
Acetic Acid, glacial	MQ	7 days/24°C (75°F)	-5	-	-	nil
	VMQ		-5	-	-	5
	PVMQ		-5	-	-	5
	FVMQ	2 days/24°C (75°F)	-	-	-	20
Hydrochloric Acid (5% in Perchloroethylene)	VMQ	1 day/100°C (212°F)	-30	-	-	100
	FVMQ		-15	-	-	10
Hydrochloric Acid (10%)	MQ	7 days/24°C (75°F)	nil	-	-	nil
	VMQ		-5	-	-	nil
	PVMQ		nil	-	-	nil
	FVMQ		-5	-25	-15	nil
Hydrochloric Acid (18%)	FVMQ	3 days/24°C (75°F)	nil	-20	-10	nil
		3 days/65°C (150°F)	nil	-35	-10	10
Hydrochloric Acid (36%, concentrated)	MQ	7 days/24°C (75°F)	PR	PR	PR	PR
	VMQ		-5	-	-	5
	PVMQ		BR	BR	BR	BR
	FVMQ		-5	-45	-30	10
Hydrofluoric Acid (48%)	PMQ	9 days/27°C (80°F)	DT	DT	DT	DT
Nitric Acid (10%)	MQ	7 days/24°C (75°F)	nil	-	-	10
	VMQ		nil	-	-	nil
	PVMQ		nil	-	-	nil
	FVMQ		nil	-10	-3	nil

* Data based on *Silastic*® NCP-80 and NCP-40 Silicone Rubber.

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
PR - poor

BR - brittle

Acids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Nitric Acid (50%)	FVMQ	3 days/24°C (75°F)	5	-15	-10	5
		3 days/65°C (150°F)	-10	-80	-30	5
Nitric Acid (70%, concentrated)	MQ	7 days/24°C (75°F)	PR	PR	PR	PR
	VMQ		5	-	-	-10
	PVMQ		BR	BR	BR	BR
	FVMQ		nil	-40	-30	5
Phosphoric Acid (10%)	MQ	7 days/24°C (75°F)	UA	UA	UA	UA
	PMQ	7 days/100°C (212°F)	UA	UA	UA	UA
	MQ		UA	UA	UA	UA
	PMQ		UA	UA	UA	UA
Phosphoric Acid (85%, concentrated)	MQ		7 days/24°C (75°F)	UA	UA	UA
	PMQ	7 days/100°C (212°F)	UA	UA	UA	UA
	VMQ		UA	-39	nil	-23
	FMQ		4	-8	-9	-2
Stearic Acid	MQ		7 days/100°C (212°F)	UA	UA	UA
	PMQ	UA		UA	UA	UA
Sulfuric Acid (20%)	MQ	1 day/83°C (180°F)	nil	-10	-5	-5
		7 days/83°C (180°F)	nil	-25	-15	-10
Sulfuric Acid (30%)	PVMQ	2 hr/93°C (200°F)	nil	-20	-5	nil
Sulfuric Acid (50%)	FVMQ	3 days/24°C (75°F)	nil	-5	-5	nil
		3 days/65°C (150°F)	5	-35	-15	nil
Sulfuric Acid (95%, concentrated)	MQ	7 days/24°C (75°F)	DC	DC	DC	DC
	VMQ		DC	DC	DC	DC
	FVMQ		DC	DC	DC	DC
	PVMQ		DC	DC	DC	DC

Bases

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Ammonium Hydroxide (saturated)	MQ	7 days/24°C (75°F)	-5	-	-	nil
	VMQ		nil	-	-	nil
	PMQ		UA	UA	UA	UA
	PVMQ		nil	-	-	0
	FVMQ		-5	-45	-5	5
Calcium Oxide (10%, saturated)	VMQ	1 day/150°C (302°F)	5	-15	-10	5
Lithium Hydroxide (2%)	VMQ	1 day/150°C (302°F)	nil	-25	-10	-5
Lithium Hydroxide (5%)	VMQ	1 day/150°C (302°F)	-10	-70	nil	-35
Lithium Hydroxide (10%, saturated)	VMQ	1 day/150°C (302°F)	DT	DT	DT	DT
Potassium Hydroxide (10%)	VMQ	1 day/150°C (302°F)	5	-20	-15	-5
Potassium Hydroxide (25%)	MQ	7 days/83°C (180°F)	nil	-	-	5
	PMQ		-5	-	-	nil
Potassium Hydroxide (saturated)	VMQ	1 day/150°C (302°F)	-20	-40	-10	-10

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
PR - poor

BR - brittle
UA - unaffected

DC - decomposed

Bases (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Sodium Hydroxide (10%)	MQ	7 days/24°C (75°F)	-5	-	-	nil
	VMQ		-5	-	-	nil
	PMQ		-	-	-	5
	PVMQ		-5	-	-	nil
	FVMQ		-5	-45	-10	nil
Sodium Hydroxide (25%)	MQ	7 days/83°C (180°F)	-5	-	-	nil
	PMQ		-5	-	-	-10
Sodium Hydroxide (50%)	VMQ	7 days/24°C (75°F)	-5	-	-	nil
	PMQ		-	-	-	10
	FVMQ		-5	-10	5	nil
	PMQ	7 days/100°C (212°F)	-	-	-	15

Salts

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Copper Sulfate (50%)	PMQ	5 days/100°C (212°F)	UA	UA	UA	UA
Ferric Chloride (60%)	MQ	7 days/100°C (212°F)	UA	UA	UA	UA
	PMQ		FR	FR	FR	FR
Sodium Carbonate (2%)	MQ	7 days/24°C (75°F)	nil	-	-	nil
	VMQ		-5	-	-	nil
	PVMQ		5	-	-	nil
Sodium Chloride (10%)	MQ	7 days/24°C (75°F)	nil	-	-	nil
	VMQ		nil	-	-	nil
	PVMQ		5	-	-	nil

Other Chemicals

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Acetonitrile	VMQ	20 hr/24°C(75°F)	-	-	-	nil
	FVMQ		-	-	-	5
	VMQ	168hr/150°C (302°F)	-	-	-	5
	FVMQ		DI	DI	DI	DI
Ammonia	MQ	7 days/24°C (75°F)	nil	-	-	nil
	VMQ		-10	-	-	nil
	PVMQ		-5	-	-	5
	VMQ	24hr/110°C(230°F)	-	260	200	-
FVMQ	300 lb. pressure	DT	DT	DT	DT	
Aniline	FVMQ	7 days/24°C (75°F)	nil	-30	-15	5
Bromine (liquid)	MQ	7 days/24°C (75°F)	25	-	-	15
Butylene Oxide	MQ	1 day/24°C (75°F)	-	-	-	20
	PMQ		-	-	-	40
Calcium Silicate (10%, saturated)	VMQ	1 day/150°C (302°F)	nil	nil	nil	5
Caprolactam Monomer	VMQ	3 days/24°C (75°F)	nil	-20	-10	nil
	FVMQ		-5	-20	nil	nil

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
UA - unaffected

FR - fair
DI - disintegrated

Other Chemicals (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
1-Chlorodecane	FVMQ	7 days/24°C (75°F)	-5	-20	-20	10
Dimethyl Formamide	FVMQ	1 day 24°C (75°F)	DT	DT	DT	DT
	MQ	7 days/24°C (75°F)	nil	-	-	2
	PMQ	7 days/24°C (75°F)	nil	-	-	2
Diethyl Phthalate	VMQ	3 days/70°C (158°F)	-1	-10	-12	10
		6 days/70°C (158°F)	-5	-16	-9	11
		70 hr/150°C (302°F)	-15	-4	8	13
	FVMQ	70 hr/150°C (302°F)	-9	-13	-13	7
Dowtherm 209 (Dow) (50/50 Water)	VMQ	14 days/100°C (212°F)	2	-7	-17	nil
Ethylene Glycol	FVMQ	7 days/24°C (75°F)	nil	-10	-10	nil
Ethylene Glycol (60%)	MQ	7 days/135°C (275°F)	-25	-	-	20
Ethylene Glycol (50%)	VMQ	7 days/83°C (180°F)	nil	nil	10	nil
	FVMQ	7 days/83°C (180°F)	nil	-5	5	nil
	VMQ	70 hr/100°C (212°F)	-1	-4	nil	1
		7 days/100°C (212°F)	-7	-5	2	nil
		14 days/100°C (212°F)	-4	-10	-12	1
	PVMQ	7 days/121 °C (250°F)	-5	-	-	5
Ethylene Glycol Mixture (1/3 Ethylene Glycol; 1/3 EthylAlcohol; 1/3 Water)	VMQ	7 days/100°C (212°F)	-1	-2	2	5
Ethylene Oxide	MQ	3 days/24°C (75°F)	-	-	-	25
	FVMQ	7 days/24°C (75°F)	-15	-75	-60	100
	VMQ	7 days/71°C (160°F)	-30	-70	-65	95
	MQ	14 days/71°C (160°F)	-	-	-	45
	PVMQ	32 hr/110°C (230°F)	nil	-25	-30	nil
Freon 11 (DuPont)	VMQ	3 days/24°C (75°F)	-	-	-	175
	PVMQ	3 days/24°C (75°F)	-	-	-	260
	FVMQ	3 days/24°C (75°F)	-	-	-	30
Freon 12 (DuPont)	VMQ	3 days/24°C (75°F)	-	-	-	150
	PVMQ	3 days/24°C (75°F)	-	-	-	195
	FVMQ	3 days/24°C (75°F)	-	-	-	45
Freon 21 (DuPont)	MQ	7 days/-55°C (-67°F)	-5	-	-	225
		7 days/24°C (75°F)	-15	-	-	165
Freon 22 (DuPont)	MQ	7 days/-55°C (-67°F)	-10	-	-	110
	FVMQ	3 days/24°C (75°F)	-	-	-	205
	MQ	7 days/24°C (75°F)	-5	-	-	75
	VMQ	7 days/24°C (75°F)	-5	-	-	75

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Other Chemicals (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Freon 113 (DuPont)	MQ	7 days/-55°C (-67°F)	-5	-	-	200
		7 days/24°C (75°F)	-5	-	-	150
Freon 114 (DuPont)	VMQ	3 days/24°C (75°F)	-	-	-	130
	PVMQ		-	-	-	135
	FVMQ		-	-	-	25
HMS 20-1083	VMQ	3 days/24°C (75°F)	-20	-	-	125
	PVMQ		-15	-	-	100
Hydrazine (Anhydrous)	FVMQ	3 days/24°C (75°F)	ES	ES	ES	ES
Hydrogen Peroxide (3%)	PMQ	7 days/24°C (75°F)	UA	UA	UA	UA
Hydrogen Peroxide (30%)	PMQ	7 days/24°C (75°F)	UA	UA	UA	UA
Hydrogen Peroxide HTP (90%)	FVMQ	7 days/65°C (150°F)	nil	-20	-15	5
Isopropyl Nitrate	FVMQ	7 days/24°C (75°F)	-	-	-	200
Methyl Methacrylate	VMQ	4 hr/25°C (77°F)	-	-	-	106
	FVMQ		-	-	-	104
Molybdenum Disulfide	VMQ	3 days/24°C (75°F)	nil	-	-	nil
	PVMQ		nil	-	-	nil
	FVMQ		nil	-	-	nil
	VMQ	3 days/150°C (302°F)	nil	-	-	nil
	PVMQ		nil	-	-	nil
	FVMQ		5	-	-	nil
Monoethanolamine	VMQ	70 hr/24°C (75°F)	nil	-20	5	nil
		70 hr/38°C (100°F)	-5	-25	5	5
	VMQ	70 hr/121°C (250°F)	-25	-80	-5	5
	FVMQ		DT	DT	DT	DT
Pentachlorophenol (10% in Ethanol)	PMQ	7 days/24°C (75°F)	-	-	-	5
Phenol (70%)	MQ	7 days/100°C (212°F)	-30	-	-	5
Phenol (85%)	MQ	7 days/24°C (75°F)	-10	-	-	10
Phthalic Acid Anhydride	MQ	7 days/149°C (300°F)	5	-	-	nil
Phthalic Anhydride	MQ	1 day/200°C (392°F)	nil	-	-	nil
	VMQ		nil	-	-	nil
	FVMQ		nil	-	-	nil
	MQ	5 days/200°C (392°F)	-2	-	-	nil
	VMQ		nil	-	-	nil
	FVMQ		-2	-	-	7
	MQ	7 days 200°C (392°F)	-2	-	-	2
	VMQ		nil	-	-	nil
	FVMQ		2	-	-	7

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
UA - unaffected

ES - excessive swell

Other Chemicals (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Polyglycol (Dow 80-6)	VMQ	7 days/24°C (75°F)	-5	-	-	5
	PVMQ		-5	-	-	5
	MQ	7 days/121°C (250°F)	-5	-	-	5
	VMQ		-10	-	-	5
Polystyrene (expandable)	VMQ	7 days/24°C (75°F)	nil	5	10	nil
Propylene Oxide	MQ	7 days/24°C (75°F)	-20	-	-	150
RX-1099 (Vinyl Plastisol)	VMQ	7 days/24°C (75°F)	-5	-	-	10
	FVMQ		-5	-	-	5
Salicylanilide (10% in 2 B Ethanol)	PMQ	7 days/24°C (75°F)	-	-	-	5
Santicizer 141 (Monsanto)	VMQ	70 hr/150°C (302°F)	DT	DT	DT	DT
	PVMQ		DT	DT	DT	DT
	FVMQ		DT	DT	DT	DT
Styrene Monomer	PVMQ	1 hr/24°C (75°F)	-10	-	-	55
		1 hr/100°C (212°F)	-20	-	-	115
Sulfur (molten)	PMQ	7 days/121°C (250°F)	UC	UC	UC	UC
	VMQ	4 days/199°C (390°F)	-22	DT	DT	DT
Sulfur Dioxide (dry gas)	MQ	7 days/24°C (75°F)	nil	-	-	nil
	VMQ		-5	-	-	nil
	PVMQ		nil	-	-	nil
Sulfur Dioxide (liquid)	MQ	7 days/24°C (75°F)	nil	-	-	5
Sulfur Hexafluoride	VMQ	1 day/150°C (302°F)	nil	-	-	nil
	FVMQ		nil	-	-	nil
	VMQ	2 days/199°C (390°F)	nil	-	-	nil
	FVMQ		5	-	-	nil
	VMQ	3 days/199°C (390°F)	nil	-	-	nil
	FVMQ		5	-	-	nil
Tar	PMQ	7 days/100°C (212°F)	nil	-	-	10
Tetrahydrofuran (Tetramethylene Oxide)	VMQ	1 day/25°C (77°F)	-	-	-	260
	FVMQ		-	-	-	170
Trichloroethylene	FVMQ	1 day/24°C (75°F)	-10	-	-	25
	MQ	7 days/24°C (75°F)	-	-	-	250
	FVMQ	5 days/49°C (120°F)	-10	-	-	20
Trifluorochloroethylene	MQ	7 days/-58°C (-65 °F)	-20	-	-	100

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
UC - unchanged

For information about silicone elastomers from the XIAMETER brand

A global leader in silicones, silicon-based technology and innovation, the XIAMETER brand from Dow Corning offers an extensive line of silicone elastomers that meet performance requirements across a wide range of industrial and consumer applications.

XIAMETER brand silicone rubber products are designed for customers who simply need an efficient way to buy reliable, high-quality standard materials at market-driven prices. For product information, visit www.xiameter.com.

LIMITED WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Dow Corning is a registered trademark of Dow Corning Corporation.
XIAMETER is a registered trademark of Dow Corning Corporation.

©2012 Dow Corning Corporation. All rights reserved.

Form No. 95-1129-01

